

Product Data Sheet

Edition 4.23.2018

SikaQuick® FNP

SikaQuick® FNP

Fast-setting, one-component, polymer-modified, self consolidating, structural repair mortar with fiber and integral corrosion inhibitor for form and pour/pumpable applications

Description	SikaQuick FNP is a self consolidating mortar for form and pour/pumping in concrete repair applications. It provides high pumpability for structural repair of columns and beams.
Where to Use	■ Horizontal, vertical and overhead repairs ■ Parking garages, bridges, beams, columns, tunnels, building facades, retaining walls and other structural applications ■ Pre-placed aggregate applications ■ Marine structures such as piers, dams, sea walls, etc.
Advantages	■ High fluidity for ease of pumping and pouring in congested repairs ■ Fiber reinforced ■ Integral corrosion inhibitor ■ One-component for easy mixing ■ Up to 8" (203mm) in thickness with aggregate - 3" (76mm) neat ■ Freeze/Thaw resistant ■ Extremely low shrinkage ■ Excellent bond strength
Coverage	~0.5 cu.ft. per 55 lb bag.
Packaging	55 lb bag; 48 bags per pallet

Typical Data (Material and curing conditions @ 73°F (23°C) and 50% R.H.)

RESULTS MAY DIFFER BASED UPON STATISTICAL VARIATIONS DEPENDING UPON MIXING METHODS AND EQUIPMENT, TEMPERATURE, APPLICATION METHODS, TEST METHODS, ACTUAL SITE CONDITIONS AND CURING CONDITIONS.

Shelf Life:	1 year in original, unopened packaging.
Storage Conditions:	Store dry at 40°-95°F (4°-35°C).
Condition material:	Condition material to 65°- 75°F before using.
Pot Life	60 minutes
Initial Set (ASTM C 266)	70-100 min
Final Set (ASTM C 266)	2-3 hours
VOC (Method EPA 24)	0 g/L

Compressive Strength (ASTM C 109)

Day 1	psi (MPa) 3,500 (24.1)
Day 7	6,000 (41.4)
Day 28	7,500 (51.7)

Flexural Strength (ASTM C 293)

Day 1	psi (MPa) 700 (4.8)
Day 7	1,300 (9)
Day 28	1,500 (10.3)

Modulus of Elasticity (ASTM C 469)

Day 28	psi 5x10 ⁶ psi
--------	-------------------------------------

Chloride Perm. (ASTM C 1202/ AASHTO T277)

< 750 coulombs

Freeze Thaw Resistance (ASTM C 666)

98%

Scaling Resistance (ASTM C 672)

0 (No Scaling)

Shrinkage (ASTM C 157 modified per ASTM C 928)

< 0.06%

Direct Bond Strength (ASTM C 1583)

500-600 psi (3.4 - 4.1 MPa)



PRIOR TO EACH USE OF ANY SIKA PRODUCT, THE USER MUST ALWAYS READ AND FOLLOW THE WARNINGS AND INSTRUCTIONS ON THE PRODUCT'S MOST CURRENT PRODUCT DATA SHEET, PRODUCT LABEL AND SAFETY DATA SHEET WHICH ARE AVAILABLE ONLINE AT [HTTP://USA.SIKA.COM/](http://usa.sika.com/) OR BY CALLING SIKA'S TECHNICAL SERVICE DEPARTMENT AT 800.933.7452 NOTHING CONTAINED IN ANY SIKA MATERIALS RELIEVES THE USER OF THE OBLIGATION TO READ AND FOLLOW THE WARNINGS AND INSTRUCTIONS FOR EACH SIKA PRODUCT AS SET FORTH IN THE CURRENT PRODUCT DATA SHEET, PRODUCT LABEL AND SAFETY DATA SHEET PRIOR TO PRODUCT USE.

How to Use

Surface Preparation

Remove all deteriorated concrete, dirt, oil, grease, and all bond-inhibiting materials from surface. Be sure repair area is not less than 1/4 in. in depth. Preparation work should be done by high pressure water blast, scabbler, or other appropriate mechanical means to obtain an exposed aggregate surface with a minimum surface profile of $\pm 1/8$ in. (CSP-7-8). Saturate surface with clean water. Substrate should be Saturated Surface Dry (SSD) with no standing water during application.

Reinforcing Steel: Steel reinforcement should be thoroughly prepared by mechanical cleaning to remove all traces of rust. Where corrosion has occurred, the steel should be high-pressure washed with clean water after mechanical cleaning. For priming and protection of reinforcing steel use Sika® Armatec® 110 EpoCem (consult Product Data Sheet).

Mixing

Start with 7/8 gal of water and add up to 1 gal per 55lbs bag in a mixing container. Add SikaQuick® FNP while continuing to mix. Mix to a uniform consistency, maximum 3 minutes. Mechanically mix with a low-speed drill (400-600 rpm) a mud paddle.

Application

- Pre-wet surface to SSD.
- Ensure good intimate contact with the substrate. To accomplish this, material should be scrubbed into the substrate or other suitable means should be employed such as vibration of the material or pumping under pressure.
- Vibrate form while pouring or pumping.
- Pump with a variable pressure pump. Continue pumping until a 3 to 5 psi increase in normal line pressure is evident, then STOP pumping.
- Form should not deflect. Vent to be capped when steady flow is evident and forms stripped when appropriate.
- For applications greater than 3" in depth, add 3/8" coarse aggregate. The addition rate is 25 lbs. of aggregate per bag of SikaQuick® FNP. (25 lbs. of 3/8" aggregate is approximately 2.0 gallons by loose volume of aggregate). The aggregate must be non-reactive (reference ASTM C-1260, C-227 and C-289), clean, well graded, saturated surface dry, have low absorption and high density, and comply with ASTM C-33 size number 8 per Table 2. Variances in aggregate may result in different strengths. No additional mix water is required.

Curing

As per ACI recommendations for portland cement concrete, curing is required. Moist cure with wet burlap and polyethylene, a fine mist of water or a water based* compatible curing compound. Curing compounds adversely affect the adhesion of following layers of mortar, leveling mortar or protective coatings. Moist curing should commence immediately after finishing. Protect newly applied material from direct sunlight, wind, rain and frost. *Pretesting of curing compound is recommended.

Limitations

- Application thickness recommended:

	Min	Max
Neat	1/4"	3"
Extended	1"	8"

- Minimum ambient and surface temperatures 40°F (4°C) and rising at time of application. Refer to the American Concrete Institute (ACI) for cold-weather or hot-weather application guidelines.
- Do not add any additives (plasticizers, accelerators, retarders, etc.) or cement to SikaQuick® FNP
- As with all cement based materials, avoid contact with aluminum to prevent adverse chemical reaction and possible product failure. Insulate potential areas of contact by coating aluminum bars, rails, posts, with an appropriate epoxy such as Sikadur® 32 Hi-Mod.
- Egg beater paddle type is not recommended for SikaQuick® FNP as it will introduce a lot of air into the mix

PRIOR TO EACH USE OF ANY SIKA PRODUCT, THE USER MUST ALWAYS READ AND FOLLOW THE WARNINGS AND INSTRUCTIONS ON THE PRODUCT'S MOST CURRENT PRODUCT DATA SHEET, PRODUCT LABEL AND SAFETY DATA SHEET WHICH ARE AVAILABLE ONLINE AT [HTTP://USA.SIKA.COM/](http://usa.sika.com/) OR BY CALLING SIKA'S TECHNICAL SERVICE DEPARTMENT AT 800.933.7452 NOTHING CONTAINED IN ANY SIKA MATERIALS RELIEVES THE USER OF THE OBLIGATION TO READ AND FOLLOW THE WARNINGS AND INSTRUCTIONS FOR EACH SIKA PRODUCT AS SET FORTH IN THE CURRENT PRODUCT DATA SHEET, PRODUCT LABEL AND SAFETY DATA SHEET PRIOR TO PRODUCT USE.

KEEP CONTAINER TIGHTLY CLOSED • KEEP OUT OF REACH OF CHILDREN • NOT FOR INTERNAL CONSUMPTION • FOR INDUSTRIAL USE ONLY

All information provided by Sika Corporation ("Sika") concerning Sika products, including but not limited to, any recommendations and advice relating to the application and use of Sika products, is given in good faith based on Sika's current experience and knowledge of its products when properly stored, handled and applied under normal conditions in accordance with Sika's instructions. In practice, the differences in materials, substrates, storage and handling conditions, actual site conditions and other factors outside of Sika's control are such that Sika assumes no liability for the provision of such information, advice, recommendations or instructions related to its products, nor shall any legal relationship be created by or arise from the provision of such information, advice, recommendations or instructions related to its products. The user of the Sika product(s) must test the product(s) for suitability for the intended application and purpose before proceeding with the full application of the product(s). Sika reserves the right to change the properties of its products without notice. All sales of Sika product(s) are subject to its current terms and conditions of sale which are available at www.usa.sika.com or by calling 800-933-7452.

Prior to each use of any Sika product, the user must always read and follow the warnings and instructions on the product's most current Product Data Sheet, product label and Safety Data Sheet which are available online at www.usa.sika.com or by calling Sika's Technical Service Department at 800-933-7452. Nothing contained in any Sika materials relieves the user of the obligation to read and follow the warnings and instruction for each Sika product as set forth in the current Product Data Sheet, product label and Safety Data Sheet prior to product use.

LIMITED WARRANTY: Sika warrants this product for one year from date of installation to be free from manufacturing defects and to meet the technical properties on the current Product Data Sheet if used as directed within shelf life. User determines suitability of product for intended use and assumes all risks. Buyer's sole remedy shall be limited to the purchase price or replacement of product exclusive of labor or cost of labor. **NO OTHER WARRANTIES EXPRESS OR IMPLIED SHALL APPLY INCLUDING ANY WARRANTY OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE. SIKA SHALL NOT BE LIABLE UNDER ANY LEGAL THEORY FOR SPECIAL OR CONSEQUENTIAL DAMAGES. SIKA SHALL NOT BE RESPONSIBLE FOR THE USE OF THIS PRODUCT IN A MANNER TO INFRINGE ON ANY PATENT OR ANY OTHER INTELLECTUAL PROPERTY RIGHTS HELD BY OTHERS.**

Visit our website at www.usa.sika.com

1-800-933-SIKA NATIONWIDE

Regional Information and Sales Centers. For the location of your nearest Sika sales office, contact your regional center.

Sika Corporation
201 Polito Avenue
Lyndhurst, NJ 07071
Phone: 800-933-7452
Fax: 201-933-6225

Sika Canada Inc.
601 Delmar Avenue
Pointe Claire
Quebec H9R 4A9
Phone: 514-697-2610
Fax: 514-694-2792

Sika Mexicana S.A. de C.V.
Carretera Libre Celaya Km. 8.5
Fracc. Industrial Balvanera
Corregidora, Queretaro
C.P. 76920
Phone: 52 442 2385800
Fax: 52 442 2250537

