

TECHNICAL DATA SHEET**DESCRIPTION**

Epoxy Rebar Spray J62 is an epoxy coating packaged in a ready to use 12 ounce spray can. The color of this epoxy coating is green.

USE

The Epoxy Rebar Spray J62 is designed as a protective coating to touch-up damaged epoxy coating, such as nicks, scratches etc., on rebar.

PROPERTIES

Dry Time @ 72°F (22°C), 50% humidity, 1.5 mil thickness:

To Touch 10 minutes

To Recoat 30 minutes

Hard Cure 48 hours

Meets ASTM D-3963 requirements regarding the repair of defects in organic coatings for rebar*.

*When applied at a wet mil thickness of 7 mils (5 mil dry)

Packaging

PRODUCT CODE	PACKAGE	SIZE	
		Ounces	Grams
69660	Spray Can (12/case)	12	340

STORAGE

The material should be stored at 40°-95°F (5°-35°C). Shelf life of properly stored, unopened containers is 24 months.

Surface Preparation:

Surface must be clean, dry and free of rust before application. Protect surrounding areas from spray mist with drop cloths, newspaper, etc. Temperature should be between 50°F and 90°F (10°C and 32°C.). For best results, can temperature should be between 70° and 80°F (21°-27°C).

Placement:

Shake can at least one minute after rattle is heard and occasionally during use. Spray surface with steady even strokes at a distance of 8 to 10 inches (20 to 25cm). Several light coats give a better finish than one heavy coat. Recoat, spray on a second coat within 30 minutes. Do not recoat after 4 hours or lifting may occur. Drying times vary with temperature, humidity and film thickness. Test a small hidden area before recoating.

CLEAN UP

To clear sprayhead for future use, turn can upside down and spray for 3 seconds. Completely empty cans may be recycled or disposed of with regular trash. Dispose of partially empty cans responsibly. DO NOT incinerate or compact.

LIMITATIONS**FOR PROFESSIONAL USE ONLY**

Store can at 40°-95°F (5°-35°C). Do not allow can to freeze. Empty can should be discarded in trash pickup.

Do not place in garbage compactor or burn.

PRECAUTIONS**READ SDS PRIOR TO USING PRODUCT**

- Use with adequate ventilation
- Wear protective clothing, gloves and eye protection (goggles, safety glasses and/or face shield)
- Keep out of the reach of children
- Do not take internally
- In case of ingestion, seek medical help immediately
- May cause skin irritation upon contact, especially prolonged or repeated. If skin contact occurs, wash immediately with soap and water and seek medical help as needed.
- If eye contact occurs, flush immediately with clean water and seek medical help as needed
- Dispose of waste material in accordance with federal, state and local requirements

MANUFACTURER

Dayton Superior Corporation
1125 Byers Road
Miamisburg, OH 45342
Customer Service: 888-977-9600
Technical Services: 877-266-7732
Website: www.daytonsuperior.com

TECHNICAL DATA SHEET**WARRANTY**

Dayton Superior Corporation ("Dayton") warrants for 12 months from the date of manufacture or for the duration of the published product shelf life, whichever is less, that at the time of shipment by Dayton, the product is free of manufacturing defects and conforms to Dayton's product properties in force on the date of acceptance by Dayton of the order. Dayton shall only be liable under this warranty if the product has been applied, used, and stored in accordance with Dayton's instructions, especially surface preparation and installation, in force on the date of acceptance by Dayton of the order. The purchaser must examine the product when received and promptly notify Dayton in writing of any non-conformity before the product is used and no later than 30 days after such non-conformity is first discovered. If Dayton, in its sole discretion, determines that the product breached the above warranty, it will, in its sole discretion, replace the non-conforming product, refund the purchase price or issue a credit in the amount of the purchase price. This is the sole and exclusive remedy for breach of this warranty. Only a Dayton officer is authorized to modify this warranty. The information in this data sheet supersedes all other sales information received by the customer during the sales process. THE FOREGOING WARRANTY SHALL BE EXCLUSIVE AND IN LIEU OF ANY OTHER WARRANTIES, EXPRESS OR IMPLIED, INCLUDING WARRANTIES OF MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE, AND ALL OTHER WARRANTIES OTHERWISE ARISING BY OPERATION OF LAW, COURSE OF DEALING, CUSTOM, TRADE OR OTHERWISE.

Dayton shall not be liable in contract or in tort (including, without limitation, negligence, strict liability or otherwise) for loss of sales, revenues or profits; cost of capital or funds; business interruption or cost of downtime, loss of use, damage to or loss of use of other property (real or personal); failure to realize expected savings; frustration of economic or business expectations; claims by third parties (other than for bodily injury), or economic losses of any kind; or for any special, incidental, indirect, consequential, punitive or exemplary damages arising in any way out of the performance of, or failure to perform, its obligations under any contract for sale of product, even if Dayton could foresee or has been advised of the possibility of such damages. The Parties expressly agree that these limitations on damages are allocations of risk constituting, in part, the consideration for this contract, and also that such limitations shall survive the determination of any court of competent jurisdiction that any remedy provided in these terms or available at law fails of its essential purpose.