

MasterEmaco® T 545DOT

Very rapid setting chemical-action repair mortar

FORMERLY SET® 45 CAL TRAN

PACKAGING

50 lb (22.6 kg) polyethylene-lined bags

YIELD

A 50 lb (22.6 kg) bag of mixed with the required amount of water produces a volume of approximately 0.39 ft³ (0.011 m³); 60% extension using ½" (13 mm) rounded, sound aggregate produces approximately 0.58 ft³ (0.016 m³).

STORAGE

Store in unopened containers in cool, clean, dry conditions

SHELF LIFE

1 year when properly stored

VOC CONTENT

0 g/L less water and exempt solvents

DESCRIPTION

MasterEmaco T 545DOT is a one-component magnesium phosphate-based patching and repair mortar. This concrete repair and anchoring material has a minimum initial set time of 15 minutes and a minimum final set time of 25 minutes @ 70° F and takes rubber tire traffic in 45 minutes.

PRODUCT HIGHLIGHTS

- Only requires the addition of potable water
- Reaches 2,000 psi compressive strength in 1 hour to rapidly return repairs to service
- Wide temperature use range from below freezing to hot weather exposures
- Very low drying shrinkage for improved bond to concrete for repair and anchoring applications
- Resistant to freeze/thaw cycles and deicing chemicals so it is usable in most environments
- Air cure only, no wet curing compounds required
- Coefficient of thermal expansion similar to Portland cement concrete for more permanent repairs
- Higher sulfate resistance than conventional mortars

APPLICATIONS

- Interior and exterior
- Horizontal and formed vertical or overhead repairs
- Applications requiring high early-strength gain
- Structural concrete repairs
- Partial and full-depth repairs
- Grouting applications such as anchor bolts, rebar, dowel rods and precast applications

SUBSTRATES

- Concrete

HOW TO APPLY

SURFACE PREPARATION

1. Concrete must be structurally sound and fully cured (28 days).
2. Saw cut the perimeter of the area being repaired into a square with a minimum depth of ½" (13 mm).
3. Refer to current ICRI Guideline no. 310.2R for surface prep requirements to permit proper bond.
4. Any surface carbonation in the repair area will inhibit chemical bonding. Apply a pH indicator to the prepared surface to test for carbonation. If carbonation is present, abrade surface to a depth that is not carbonated.

Technical Data

Composition

MasterEmaco T 545DOT is a magnesium-phosphate patching and repair mortar.

Test Data

PROPERTY	RESULTS	TEST METHOD
Compressive strength, psi (MPa), 3 hour 24 hour	 4,000 (27.6) 5,200 (35.9)	California Test 551 - Section 1
Flexural Strength, psi (MPa), 24 hours	 525 (3.6)	California Test 551 - Section 4
Bond Strength, psi (MPa), SSD Bond Strength @ 24 hours Dry Bond Strength @ 24 hours	 350 (2.4) 420 (2.9)	California Test 551 - Section 5
Water Absorption, %	9	California Test 551 - Section 8
Abrasion Resistance, grams 24 hours	 21 grams	California Test 550
Drying Shrinkage, % 4 days	 0.05	ASTM C 596
Soluble Chlorides by weight, %	0.03	California Test 422
Water Soluble Sulfates by weight, %	0.15	California Test 417

* All tests were performed with neat material (no aggregate)
 Test results are averages obtained under laboratory conditions. Expect reasonable variations.

MIXING

1. MasterEmaco T 545DOT must be mixed, placed, and finished within 15 minutes in normal temperatures (72° F [22° C]). Only mix quantities that can be placed in 15 minutes or less.
2. Do not deviate from the following sequence; it is important for reducing mixing time and producing a consistent mix. Use a minimum ½" slow-speed drill and mixing paddle or an appropriately sized mortar mixer. Do not mix by hand.
3. Pour potable water into mixer. Water content is critical. Use a maximum of 4 pts (1.9 L) of water per 50 lb (22.6 kg) bag of MasterEmaco T 545DOT. Do not deviate from the recommended water content.
4. Add the powder to the water and mix for approximately 2½ to 3 minutes.
5. Use neat material for patches from ½–2" (13–51 mm) in depth or width. For deeper patches, extend a 50 lb (22.6 kg) bag of MasterEmaco T 545 HT by adding up to 30 lbs (13.6 kg) of properly graded, dust-free, hard, rounded aggregate or noncalcareous crushed angular aggregate, not exceeding ½" (13 mm) in accordance with ASTM C 33, #8. If aggregate is damp, reduce water content accordingly. Special procedures must be followed when angular aggregate is used. Contact your local Master Builders Solutions representative for more information. (Do not use calcareous aggregate made from soft limestone. Test aggregate for fizzing with 10% HCL). Please refer to MasterEmaco T 545 HT product data guide for further information.
Note: Aggregate addition can affect compressive strength. Testing with the locally sourced aggregate is required to fully evaluate its effect on compressive strength.

APPLICATION

1. Immediately place the mixture onto the properly prepared substrate. Work the material firmly into the bottom and sides of the patch to ensure good bond.
2. Level the MasterEmaco T 545DOT and screed to the elevation of the existing concrete. Minimal finishing is required. Match the existing concrete texture.

CURING

No curing is required, but protect from rain immediately after placing. Liquid-membrane curing compounds or plastic sheeting may be used to protect the early surface from precipitation, but never wet cure.

FOR BEST PERFORMANCE

- Color variations are not indicators of abnormal product performance.
- Do not add sand, fine aggregate, or Portland cement.
- Do not use MasterEmaco T 545DOT for patches less than ½" (13 mm) deep.
- Do not use limestone aggregate.
- Do not deviate from the recommended water content printed on the bag.
- Precondition these materials to approximately 70° F (21° C) for 24 hours before using.
- Protect repairs from direct sunlight, wind, and other conditions that could cause rapid drying of material.
- When mixing or placing in a closed area, provide adequate ventilation.
- Do not use a precision machinery grout.
- Prevent any moisture loss during the first 3 hours after placement. Protect MasterEmaco T 545DOT with plastic sheeting or a curing compound in rapid-evaporation conditions.
- Do not wet cure.
- When using in contact with galvanized steel or aluminum, consult your local Master Builders Solutions sales representative.
- Do not mix partial bags
- Make certain the most current versions of product data sheet and SDS are being used; visit www.master-builders-solutions.com/en-us to verify the most current versions.
- Proper application is the responsibility of the user. Field visits by Master Builders Solutions personnel are for the purpose of making technical recommendations only and not for supervising or providing quality control on the jobsite.

HEALTH, SAFETY AND ENVIRONMENTAL

Read, understand and follow all Safety Data Sheets and product label information for this product prior to use. The SDS can be obtained by visiting www.master-builders-solutions.com/en-us, e-mailing your request to mbsbscst@mbcc-group.com or calling 1(800)433-9517. Use only as directed.

IN CASE OF EMERGENCY: Call CHEMTEL +1 (800) 255-3924 or if outside the US or Canada, +1 (813) 248-0585.

LIMITED WARRANTY NOTICE

Master Builders Solutions Construction Systems US, LLC ("Master Builders") warrants this product to be free from manufacturing defects and to meet the technical properties on the current Technical Data Guide, if used as directed within shelf life. Satisfactory results depend not only on quality products but also upon many factors beyond our control. MASTER BUILDERS MAKES NO OTHER WARRANTY OR GUARANTEE, EXPRESS OR IMPLIED, INCLUDING WARRANTIES OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE WITH RESPECT TO ITS PRODUCTS. The sole and exclusive remedy of Purchaser for any claim concerning this product, including but not limited to, claims alleging breach of warranty, negligence, strict liability or otherwise, is shipment to purchaser of product equal to the amount of product that fails to meet this warranty or refund of the original purchase price of product that fails to meet this warranty, at the sole option of Master Builders. Any claims concerning this product must be received in writing within one (1) year from the date of shipment and any claims not presented within that period are waived by Purchaser. MASTER BUILDERS WILL NOT BE RESPONSIBLE FOR ANY SPECIAL, INCIDENTAL, CONSEQUENTIAL (INCLUDING LOST PROFITS) OR PUNITIVE DAMAGES OF ANY KIND.

Purchaser must determine the suitability of the products for the intended use and assumes all risks and liabilities in connection therewith. This information and all further technical advice are based on Master Builders'

present knowledge and experience. However, Master Builders assumes no liability for providing such information and advice including the extent to which such information and advice may relate to existing third party intellectual property rights, especially patent rights, nor shall any legal relationship be created by or arise from the provision of such information and advice. Master Builders reserves the right to make any changes according to technological progress or further developments. The Purchaser of the Product(s) must test the product(s) for suitability for the intended application and purpose before proceeding with a full application of the product(s). Performance of the product described herein should be verified by testing and carried out by qualified experts.

FOR PROFESSIONAL USE ONLY. NOT FOR SALE TO OR USE BY THE GENERAL PUBLIC.